

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-329720

(43)Date of publication of application : 29.11.1994

(51)Int.Cl.

C08F 8/24

(21)Application number : 05-122856

(71)Applicant : KAO CORP

(22)Date of filing : 25.05.1993

(72)Inventor : ITO KOJI


NAKAMURA GENICHI

AMIYA TSUYOSHI

## (54) POLYETHYLENE MACROMONOMER AND ITS PRODUCTION

### (57)Abstract:

PURPOSE: To produce, in a high yield, a new high-purity polyethylene macromonomer which has a terminal (meth)acryloyl group and can be copolymerized with another vinyl monomer to give a comb-type graft polymer suitable as a polymer blend compatibilizer, a surface modifier, etc.



CONSTITUTION: Ethylene is subjected to living polymn. using a 1-6C linear or branched alkylolithium/tert. diamine initiator, reacted with a specific carbonyl compd. or oxidized with oxygen, and reacted with a (meth)acrylic acid halide to give a polyethylene macromonomer of the formula (wherein R1 is a 1-6C linear or branched satd. hydrocarbon group; R2 and R3 are each H or a 1-18C aliph. or

arom. hydrocarbon group provided R1, R2, and R3 are the same or different from each other; R4 is H or methyl; and n is an integer of 10-1,000).

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]